### **SUPRANOX 309L**



# MMA Electrodes Stainless and Heat resistant steels

SUPRANOX 309L is a semi-basic MMA electrode depositing a low C - 22/24%Cr - 12/14%Ni weld metal with approx. 12% delta-ferrite promoting high resistance to hot cracking. This electrode has three main applications:

- Buffer layers and claddings on unalloyed and low-alloy steels which are already corrosion resistant in the first layer.
- Dissimilar joints (austenitic steels to ferritic steels) with operating temperatures UP to 300°C. In case of higher temperatures, use SUPRANEL 182.
- Welding of stainless steels of similar composition.

This electrode offers excellent operability and is particularly suitable for downhand butt and fillet welding applications, the 2.5mm and 3.2mm diameter electrodes can be used for positional welding.

Exhibits a stable spray arc transfer resulting in excellent weld bead shape and appearance with a slight concave profile in horizontal vertical fillet welds. There is very little spatter and in combination with the self-releasing slag, post welding cleaning time is maintained to a minimum. Easy arc striking and restriking. Suitable for use with either AC [minimum OCV 50V] or DC positive. Efficiency 100%.

Semi-basic electrode for welding austenitic stainless steels containing 22% Cr and 12% Ni.

Classification				
EN ISO	3581-A: E 23 12 L R 12			
AWS	A5.4: E 309L-17			

Approvals	Grade
ABS	E309L-16
BV	UP
DB	•
DNV	309L

Approvals	Grade
GL	4332
LRS	SS/CMn
TÜV	•
CE	

#### **Chemical analysis (Typical values in %)**

C	Mn	Si	P	S	Cr	Ni	Ferrite
≤ 0.040	0.9	0.9	≤ 0.025	≤ 0.025	23.5	12.2	5-20

#### **All-weld metal Mechanical Properties**

Heat Treatment	Yield Strength	Tensile Strength	Elongation	Impact Energy ISO - V (J)		
iigat iigatiiigiit	(MPa)	(MPa)	A5 (%)	20 °C		
As Welded	≥ 400	≥ 520	≥ 30	≥ 47		

#### **Materials**

ASTM A249, A312, A409, A814 Grad TP309, TP309S


AISI 309-309S

#### **Storage**

Keep dry and avoid condensation.

Re-drying not generally required.

If necessary 250°-300°C for 1 hour, 5 times max.



www.oerlikon-welding.com

# **SUPRANOX 309L**



MMA Electrodes Stainless and Heat resistant steels

## **Packaging data**

Diam.	Length	Current	Approx. weightn(kg/1000)	CBOX		VPMD		
(mm)	(mm)	(A)		PC	Code	PC	Code	
2.5	300	55-80	19.3	190	W000375906	90	W000375900	
3.2	350	70-110	36.2	120	W000375907	55	W000375902	
4.0	350	120-140	54.1	80	W000375909	40	W000375903	
5.0	350	145-180	86.6	50	W000375912	20	W000375904	

2/2